



BURST

ADD-A-PAK ACCELERATOR ADDITIVE FOR PORTLAND CEMENT MORTARS

- Reduces set time
- Easy to use
- Does not affect mortar characteristics
- Cuts work time in half
- Excellent for repair work
- More economical than standard rapid setting mortars



1. Product Name

Burst

2. Manufacturer

Parex USA, Inc.

2150 Eastridge Ave, Riverside, CA 92507
866-516-0061 • www.merkrete.com

3. Product Description

Basic Use

Burst Add-A-Pak is a powerful additive giving Portland cement products a burst of accelerant for faster set times. It helps speed up work times in Portland cement mortar for mud beds, masonry mortars, underlayment, thinsets and grouts.

4. Technical Data

Applicable Standards: Merkrete standards do not apply for this product.

Packaging

1-lb. bags; 30 bags per Case | Color: Off White

Shelf Life

One year from manufacturing in sealed original container, when properly stored at room temperature off the ground in a controlled, dry area.

PRODUCTS	PRODUCT WEIGHT	WITHOUT "BURST"
700 - Non-Modified	50 lb.	7 Hours
705, 710 and 7D10 - Modified	50 lb.	7 Hours
735, 820, 855 and 856 - Highly Modified	50 lb.	7 Hours
Integra, Versatile, Sanded and Non Sanded Grouts	25 lb.	6 Hours
Underlayment 1" Thick	25 lb.	8 Hours
Mud Bed 1" Thick	50 lb.	8 Hours
AVERAGE SET TIMES*		
With "Burst" (One Packet)	With "Burst" (Two Packets)	
2.5 Hours	1 hour	
3.5 Hours	2.5 hour	
4.5 Hours	2.5 hour	
1.5 Hours	1 hour	
4 Hours	2 hour	
2 Hours	1 hour	

*at 70° F and 50% relative humidity



5. Installation

Thinset Installation - Mixing Thinset with Burst Add-a-Pak

Mix in a clean container that is to be used with the thinset. Add water first, then Burst; mix thoroughly. Add desired product as normal and mix per manufacturer's requirements. NOTE : One or two packages of BURST may be added as necessary. Always try one first, then on subsequent mixes add as desired. Mix thoroughly by hand or with a slow speed mixer to a smooth, thick, trowelable consistency. Allow mortar to slake for approximately 5 minutes. Remix before using without adding more water, latex or powder. Mortar consistency shall be such that when applied with the recommended notched trowel to the substrate, the ridges formed in the mortar do not flow or slump. During use, stir mortar mix occasionally. Do not temper with additional water.

Application of Thinset with Burst Add-a-Pak

Apply mortar to the substrate with the flat side of the trowel using enough pressure to firmly work into the surface. With a notched trowel, immediately follow with a heavier coat of material using enough mortar to provide 100% coverage to the back of the tile. For some extruded or lug back tiles, back-buttering of tiles may be required. Do not spread more mortar than can be covered in 10 minutes or before the mortar skins over. It is advised that during the installation, remove a tile to ensure the mortar has not skinned over and check the tile and substrate mortar coverage. Comb the mortar using an appropriate notched trowel in one direction. Place tiles in mortar, slide back and forth perpendicular to the ridges to ensure proper coverage. Do not adjust tiles set in mortar after 5 minutes.

Grout Installation - Mixing Color Grout with Burst Add-a-Pak

To minimize color variation when using multiple containers of the same color grout with different batch numbers, dry-blend Burst Add-a-Pak to the color grout prior to mixing with water. Combine approximately 4½ pints (2.13 l) of cool, clean water per 25-lb. (11.34-kg) bag of grout with a margin trowel or a low-speed mixer (less than 300 rpm) to a lump-free, paste-like consistency. Let stand 10 minutes and remix before use. Periodic mixing during application keeps grout workable, but do not add more water or additive once mixed. Maintaining a consistent mixing ratio between batches helps maintain color shade uniformity. Discard grout when it becomes too stiff to work.

Application of Color Grout with Burst Add-a-Pak

Installation shall conform to ANSI A108.10 - 1999. Holding a rubber grout float at a 45° angle, force grout diagonally into joints, ensuring joints are completely filled. Remove excess grout using edge of float held at a 90° angle. Cleanup can begin as soon as grout becomes firm enough to be only slightly indented when pushed. Use as little water as possible for grout cleanup. Excess water will cause variation in color and may cause shrinkage, cracks or pinholes. Smooth and level joints and, in a circular motion, remove excess grout from tile with a damp small-pore grout-sponge. It is best to change cleaning water and rinse sponge frequently. Using clean water and sponge will enhance color uniformity.

Limitations

Do not use Merkrete Burst Add-a-Pak below 40°F (4°C). Use caution to not allow mortar to freeze for the first 72 hours. Cool and wet weather may delay the set times of the Burst Add-a-Pak. Do not soak tiles before installation. Merkrete Burst Add-a-Pak mixed thinsets must not be used to apply over asphalt sheeting, vinyl covered wall board, Masonite®, cement asbestos board, metal, glass, plastic, gypsum mortar beds or other unstable substrates. Improperly cured or wet plywood, particle board or strip wood are not suitable substrates. For installations that will be continually wet like swimming pools, fountains and gang showers, the completed installation should be cured a minimum of 14 days and allowed to dry before exposure to water. For white or light colored marbles use Merkrete Burst Add-a-Pak mixed with white thinset mortar. Some dimensional stone tile like resin-backed, black, green and red marbles may warp when installed with water-based setting materials. These water-sensitive stone tiles should be installed with Merkrete Pro Epoxy. For use of Merkrete Burst Add-a-Pak mixed with thinsets, grouts and underlayment not mentioned in these instructions, contact Merkrete Technical department.

Cleaning

Water is all that is needed to remove any uncured mortar from tiles, tools and equipment.

6. Availability

Merkrete Burst Add-a-Pak is available at leading tile houses and construction distributors. Contact Merkrete or visit our website for the name of the nearest dealer at www.merkrete.com.

7. Warranty

5-year to limited lifetime warranties are available. Contact Merkrete Technical Services or visit our website for specific warranty information. Merkrete warrants that this product meets applicable ANSI standards in force at the time of manufacture.

8. Maintenance

None required, but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

9. Technical Services

Merkrete Systems maintains technical field representatives available throughout the country. Call Technical Services at 800-226-2424 for the nearest representative.

10. Literature

For the most up-to-date technical information (details, submittals, SDSs or data sheets), refer to our websites www.parexusa.com or www.merkrete.com.



BURST



Corporate Office
2150 Eastridge Ave
Riverside, CA 92507

www.merkrete.com
866-516-0061

Tech Support: 800-226-2424

PAREXUSA

Parex USA, Inc., a California Corporation

© Parex USA, Inc • December 2021 • ME FG DS 1221